

Product Description

Paraseal® GM/LG – 20 mil is a sheet waterproofing and methane-mitigating membrane consisting of 20 mils of HDPE, expandable, granular bentonite and a protective layer of spun-bonded polyester. The composite weight of the material is up to 1.0 lb/ft², creating a dual waterproofing system. The HDPE extends beyond the bentonite on the perimeter edges to create a clean surface for Para JT™ Tape and Parastick 'n' Dry® Tape installation.

Basic Uses

Paraseal GM/LG – 20 mil is designed for use in post-installation submerged conditions, on blindside walls, shotcrete walls and under slab where hydrostatic water head and/or methane conditions exist. It may also be used on backfilled walls.

Features and Benefits

- The Paraseal GM/LG – 20 mil system combines the dual waterproofing system, Para JT Tape seam tape and Parastick 'n' Dry Tape to create a robust yet flexible, waterproof and methane-mitigating membrane.
- The nature of the Paraseal waterproofing system also allows for installation over green or damp surfaces accelerating the construction process.
- The bentonite can expand up to 8 times its original thickness to stop water that may make it past the HDPE layer, providing a second layer of protection.

Availability

Paraseal GM/LG 20-mil is immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Packaging

4' x 24' (1.2 M x 7.3 M) rolls
20 rolls/pallet

Storage

Protect from moisture. Store on a skid or pallet and cover with polyethylene or tarp. Do not double stack pallets. Prevent hydration of bentonite until the sheet is installed and under recommended compaction.

Limitations

- Paraseal products require a minimum of 24 psf of compaction/confinement.
- Paraseal GM/LG – 20 mil is not to be installed over ponding or standing water or snow.
- If ground water is brackish, please contact your local Tremco Sales Representative four weeks prior to a pending application, and provide a water and/or soil sample for testing purposes in order to determine the correct bentonite formula for your project's application.
- If backfill contains substantial amounts of either lava rock, basalt or any other coarse or highly abrasive materials, a protection course or drainage mat may be required. Contact your local Tremco Sales Representative or Technical Service at 866-209-2404 for details.
- Use of Paraseal GM/LG - 20 mil in post-installation, submerged conditions requires prior approval from Tremco.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION		
Color (Bentonite/HDPE)	Gray/Black		
Installation Temperatures	-25 to 130 °F (-31.7 to 54.4 °C)		
Freeze/Thaw Cycles	No effect before or after installation		
Resistance to Chemicals & Gases	Extremely high resistance. Contact Tremco for specific information.		
Life Expectancy	Indefinite		
PROPERTY	TEST METHOD	VALUES US	VALUES SI
Elongation	ASTM D412 Type 4 Dumbbell	500%	
Strength at Break	ASTM D412	4,000 lb/in ²	281.22 kg/cm ²
Strength at Break	ASTM D6693, Type IV	80 lb/in	14.28 kg/cm
Resistance to Micro-organisms (bacteria, fungi, mold, yeast)	ASTM D4068	Unaffected	
Index Puncture Resistance	ASTM D4833	36.67 lb/ft	54.57 kg/M
Resistance to Hydrostatic Head Pressure	ASTM D5385	231' of H ₂ O	
Hydrostatic Resistance (with Para JT™ Tape)	ASTM D5385	>100 psi (>231 ft/H ₂ O)	>68.9 N/cm ² >70.4 M/H ₂ O
Permeance	ASTM E96	0.029 US Perms	1.7 ng/Pa·s·m ²
Puncture Resistance (load)	ASTM E154	155 lbf	689.47 N
All data based on 20-mil HDPE			

0316/PARAGMLG20DS-BG

3735 Green Rd
 Beachwood OH 44122
 216.292.5000 / 800.321.7906

1451 Jacobson Ave
 Ashland OH 44805
 419.289.2050 / 800.321.6357

220 Wicksteed Ave
 Toronto ON M4H1G7
 416.421.3300 / 800.363.3213

1445 Rue de Coulomb
 Boucherville QC J4B 7L8
 514.521.9555

Tremco Commercial Sealants & Waterproofing

