

TREMproof® 6100

Multi-Layered, Fabric-Reinforced, Hot-Applied, Rubberized Asphalt Waterproofing Membrane

Product Description

One-part, 100% solids, hot-applied, rubberized asphalt waterproofing membrane. TREMproof 6100 can be formulated with up to 25% recycled content. Contact your local Tremco Sales Representative for additional information.

Basic Uses

TREMproof 6100 is ideally suited for new and remedial waterproofing applications. The TREMproof 6100 system is applied to horizontal concrete surfaces and can be applied to the top level of structures, such as roof decks and unexposed top-level parking areas. TREMproof 6100 can also be used in the following applications: planters, pavers, plaza decks, vegetated roofing systems and submerged conditions.

EQUIPMENT: Heating of TREMproof 6100 is accomplished utilizing a double-jacketed, oil-bath melter with mechanical agitation, specifically designed for applying non-direct fired hot rubberized asphalt waterproofing membranes. An air jacketed melter is also acceptable. Melter must be capable of maintaining material temperature at 375 to 425 °F (191 to 218 °C), and an oil-bath temperature of 500 to 550 °F (260 to 288 °C) intermittently. Direct fired melters are not recommended.

Availability

Immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit www.tremcosealants.com.

Coverage Rates

90 mils = 0.621 lb/ft² (3.03 kg /M²)

125 mils = 0.8625 lb/ft² (4.21 kg/M²)

200 mils = 1.38 lb/ft² (6.74 kg/M²)

215 mils = 1.48 lb/ft² (7.23 kg/M²)

Packaging

50-lb (22.7-kg) boxes, 40 boxes/pallet totaling 2000 lbs (908 kg)

Sold in pallet quantities only.

Colors

Black

Applicable Standards

TREMproof 6100 meets or exceeds the following specifications and approvals:

- CGSB 37.50-M89
- Miami-Dade County Approved - NOA#09-1110.05
- Los Angeles Approved - RR#25299
- New York City Approved - MEA#62-95-5

Fire Rated Systems

- UL Class A - R-10845
- ISO 9001: 2000 Certified
- BBA Agreement Certification

Limitations

- Do not apply over any type of lightweight concrete without prior written approval from Tremco.
- Not for use on wet or frozen substrates.
- Not suitable for direct contact with coal tar derivative materials. If this condition exists on a jobsite, contact Tremco Technical Service for additional instructions.
- Concrete must be allowed to cure for a minimum of 28 days prior to application.

Warranty

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TREMproof® 6100

Multi-Layered, Fabric-Reinforced, Hot-Applied, Rubberized Asphalt Waterproofing Membrane

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	
Type	Hot-applied rubberized asphalt	
Color	Black	
Solids	100%	
Density	1.29	
Application	Flat Squeegee	
Cure Time	24 hr	
Thickness	Minimum 215 mils (wet), 215 mils (dry)	
PROPERTY	TEST METHOD	TYPICAL VALUES
Maximum V.O.C.	Method 310	0 g/L
Flash Point	ASTM D92 Minimum 500 °F (260 °C)	604 °F (318 °C)
Cone Penetration at 77 °F (25 °C), 0.43" (11.0 mm) maximum at 122 °F (50 °C), 0.78" (20.0 mm) maximum	ASTM D5329 at 77 °F (25 °C) at 122 °F (50 °C)	0.22" (5.7 mm); 0.71" (18.1 mm)
Water Vapor Permeance ng/Pa*s*m ² maximum	ASTM C836; ASTM E96 Dry Cup	0.3 ng/Pa*s*m ²
Toughness at 77 °F (25 °C), 5.5 J minimum	CAN/CGSB 37.50-M89; Section 4.4	14.9 J
Ratio of Toughness to Peak Load at 77 °F (25 °C), 0.04 minimum	CAN/CGSB 37.50-M89; Section 4.5	0.04
Adhesion Rating	CAN/CGSB 37.50-M89; Section 4.6	Pass
Water Absorption 0.012 oz (0.35 g) maximum	CAN/CGSB 37.50-M89; Section 4.8	0.007 oz (0.20 g)
Pinholing 1 pinhole maximum	CAN/CGSB 37.50-M89; Section 4.9	0
Low Temperature Flexibility	CAN/CGSB 37.50-M89; Section 4.10	Pass
Low Temperature Crack Bridging	CAN/CGSB 37.50-M89; Section 4.11	Pass
Flow	ASTM D5329	0
Heat Viscosity	CAN/CGSB 37.50-M89	11 sec

1119-1/TP6100DS-BG

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.955

**Tremco Commercial Sealants & Waterproofing**

